

Tefzel™ ETFE HT-2185

Fluoroplastic Resin

Product Information

Description

Tefzel™ ETFE HT-2185 is a special purpose fluoroplastic resin available in translucent, 2.5-mm (0.1-in) pellets. Compared with other grades of Tefzel™, it has a higher flow rate.

Tefzel™ ETFE HT-2185 and the other Tefzel™ fluoroplastics are melt processible, modified copolymers of ethylene and tetrafluoroethylene. They are high-performance resins that can be processed at relatively high rates compared with fluorocarbon resins. They are mechanically tough and offer an excellent balance of properties. Table 1 shows typical property data for Tefzel™ ETFE HT-2185.

The relatively high flow rate of Tefzel™ ETFE HT-2185 makes it uniquely suitable for high-speed processing, especially for extruded coatings and injection molding of slender, thin-walled, or intricate shapes. Molded or extruded products made from Tefzel™ ETFE HT-2185 are preferred for uses that do not involve significant flexural or tensile stress at elevated temperatures. Higher viscosity products such as Tefzel™ ETFE HT-2181 and Tefzel™ ETFE HT-2183 are preferred for these applications.

Properly processed products made from neat Tefzel™ ETFE HT-2185 are inert to most solvents and chemicals, hydrolytically stable, and weather-resistant. The recommended upper service temperature is 150°C (302°F); useful properties are retained at cryogenic ranges. The level and stability of dielectric properties are excellent, and the flame rating is V-0 by the UL94 method. Mechanical properties include outstanding impact strength, cut-through, and abrasion resistance.

Statements, or data, regarding behavior in a flame situation are not intended to reflect hazards presented by this or any other material when under actual fire conditions.

Processing

Tefzel™ ETFE HT-2185 can be processed by conventional melt extrusion techniques and injection, compression, transfer, and blow-molding processes. Compared with other grades of Tefzel™, it can be processed with greater ease and speed, because of its high flow rate. Also, the melt viscosity of Tefzel™ is reduced with increasing shear rate; thus, permitting the use of pressure extrusions through narrow dies without requiring appreciable draw-down. Reciprocating screw injection molding machines are preferred. Corrosion-resistant metals should be used in contact with molten resin. Extruder barrels should be long, relative to diameter, to provide residence time for heating the resin to approximately 340°C (640°F).

Typical End Products

Tefzel™ ETFE HT-2185 is ideal for many end products, including electrical components, such as sleeving, coil forms, sockets, connectors, and switches; lab ware, such as tubing, valves, containers, and fasteners; battery or instrument components that require chemical inertness; and mechanical parts.

Safety Precautions

Before using Tefzel™ ETFE HT-2185, refer to the Safety Data Sheet and the latest edition of "The Guide to the Safe Handling of Fluoropolymer Resins," published by The Society of the Plastics Industry, Inc. (www.fluoropolymers.org) or by PlasticsEurope (www.plasticseurope.org).

Open and use containers only in well-ventilated areas using local exhaust ventilation (LEV). Vapors and fumes liberated during hot processing, or from smoking tobacco or cigarettes contaminated with Tefzel™ ETFE HT-2185, may cause flu-like symptoms (chills, fever, sore throat) that may not occur until several hours after exposure and typically pass within about 24 hr. Vapors and fumes liberated during hot processing should be exhausted completely from the work area; contamination of tobacco with polymers should be avoided.

Mixtures with some finely divided metals, such as magnesium or aluminum, can be flammable or explosive under some conditions.

Storage and Handling

The properties of Tefzel™ ETFE HT-2185 resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and formation of water on the resin when it is removed from containers.

Packaging

Tefzel™ fluoroplastic resins are packaged in 20.3-kg (45-lb) plastic bags.

Table 1. Typical Property Data for Tefzel™ ETFE HT-2185 Fluoroplastic Resin

Property	Test Method*	Unit	Value
Thermal			
Nominal Melting Point	D3418	°C (°F)	255–280 (491–536)
Flow Rate	D3159	g/10 min	11
Upper Service Temperature	UL746	°C (°F)	155 (311)
Mechanical			
Tensile Strength, 23°C (73°F)	D638	MPa (psi)	40 (6,000)
Specific Gravity	D792	—	1.7
Ultimate Elongation, 23°C (73°F)	D638	%	300
Flexural Modulus, 23°C (73°F)	D790	MPa (psi)	1,000 (145,000)
Impact Strength, 23°C (73°F)	D256	J/m (ft-lb/in)	No Break
Comprehensive Strength	D695	MPa (psi)	38 (5,500)
Linear Coefficient of Expansion, 0–100 °C (32–212 °F)	D696	mm/mm/°C (in/in/°F)	12.6 x 10 ⁻⁵ (7.0 x 10 ⁻⁵)
Electrical			
Dielectric Strength, 0.25 mm (0.010 in)	D150	kV/mm (V/0.001 in)	70 (1,800)
Dielectric Constant, 1 MHz, 23 °C (73 °F)	D1531	—	2.5–2.6
Dissipation Factor, 1 MHz, 23 °C (73 °F)	D1531	—	0.0054
Volume Resistivity	D257	ohm-m (ohm-cm)	1 x 10 ¹⁵ (1 x 10 ¹⁷)
General			
Water Absorption, 24 hr	D270	%	0.007
Weather and Chemical Resistance	—	—	Excellent
Limiting Oxygen Index	D2863	%	30–32
Bulk Density	Chemours	g/L	1,300
Flame Rating	UL94	—	V-0

*ASTM method, unless otherwise specified

Typical properties are not suitable for specification purposes.

Tefzel™ ETFE HT-2185 meets the requirements of ASTM D3159, Type I, Grade 1.

HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Tefzel™ is a registered trademark of Chemours for its brand of ETFE fluoroplastic resins. The Tefzel™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Tefzel™ brand name as Chemours does not sell such offerings with the Tefzel™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Tefzel™ trademark from buying from Chemours, a Chemours customer or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Tefzel™ brand, please visit teflon.com/license

CAUTION: Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/tefzel

For sales and technical support contacts, visit teflon.com/industrialglobalsupport

© 2023 The Chemours Company FC, LLC. Teflon™, Tefzel™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-27430

C-10197 (8/23)